


Description:

POLYONICS PT-813 is a 7.5 mil (190 μm) thermally conductive, double coated bonding tape with silicone pressure sensitive adhesives (PSA) and fluorinated PET liners.



Features:

- High thermal impedance
- High dielectric strength
- UL94 VO flame retardant (UL recognition pending)
- REACH and RoHS compliant
- Halogen-free

Technical Data

	Property	Method	Average Results	
PHYSICAL	Color	Visual	Black	
	Total Thickness¹ inch (mm)	ASTM D-1000	0.0075 (0.19)	
	Reinforcement Carrier	-	1.5 mil Kapton MT+ Polyimide	
	Thickness TIM inch (mm)	ASTM D-1000	0.003 (0.08) each side	
	Continuous Use Temp², °C (°F)	Polyonics (1000 hrs)	0°C to 200°C (32°F to 392°F)	
	Condition Rating² -High Temp testing of solid state devices for 1000hrs	JEDEC 22-A103C	Condition D	
	Outgassing	ASTM E-595 24hrs at 125 °C	TML= 1.40% CVCM= 0.29% WVR= 0.19%	
THERMAL	Thermal Resistance³ (°C-in ² /W)	ASTM 5470 (post 1000hr @ max temp)	10 psi	0.72
			50 psi	0.64
			100 psi	0.58
MECH	Adhesion (oz/in) 180° peel strength on Aluminum w/ 24 hr dwell	Polyonics 80313	30	
	Lap Shear (psi)	ASTM D1002	13	
	Probe Tack (g/in)	ASTM D2927	77	
ELEC	Voltage Breakdown⁴ (Vac)	ASTM D149	5800	
	Vol. Resistivity^{4,5} (Ω/cm)	Polyonics Method	4x 10 ¹¹	
	Flame Rating⁶	UL-94 ^f	V-0	

¹ Does not include double liners, which add 4-4.5 mil thickness total.

² 1000 hrs at max temperature rating as tested by JESD22-A103E conditions. Cond E= +250°C, Cond D= +200°C, Cond C=+175°C

³ 8.0cm² test head

⁴ Not recommended for applications that require electrical isolation

⁵ Volume Resistivity is tested per Polyonics method, not per ASTM D149, which is designed for electrically isolating materials

⁶ Tested to the UL94 standard by Polyonics



POLYONICS

Thermal Interface Material

PT-813

Thermally Conductive Bonding Tape

NOTE: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by POLYONICS customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact POLYONICS for further information.

References: ASTM: American Society for Testing and Materials (U.S.A.) SI: International Systems of Units.

Polyonics Material Compliance

RoHS (Restriction of Hazardous Substances) EU Directive 2002/95/EC	Limits set forth in Directive 2005/618/EC amending Directive 2002/95/EC
REACH (Registration Evaluation and Authorization of Chemicals) EU Directive 1907/2006/EC	Limits set forth in Directive 1907/2006/EC Article 7 (2)
Halogen Free - Restriction use of Halogen (IEC 61249-2-21)	Limits set forth in International Electrochemical Commission

WARRANTY-LIMITATION

Polyonics' products are sold with the understanding that the Buyer will test them in actual use and determine for him/herself their adaptability to his/her intended uses. Polyonics warrants to the buyer that its products are free from defects in material and workmanship, but limits its obligations under this warranty to replacement of the products shown to Polyonics' satisfaction to have been defective, provided that the Buyer has complied with the handling, storage and shelf life requirements as specified by Polyonics in applicable materials specifications.

The above warranties extend solely to Buyer and all warranty claims must be made by the Buyer. Rework or Replacement shall neither exceed nor decrease the original warranty period. The term of all warranty periods shall not exceed thirty (30) days from the date of the original shipment.

THE ABOVE WARRANTIES ARE EXCLUSIVE OF AND IN LIEU OF ALL OTHER WARRANTIES, WRITTEN OR ORAL, EXPRESS OR IMPLIED, STATUTORY OR OTHERWISE. NO IMPLIED STATUTORY WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE SHALL APPLY. POLYONICS SHALL NOT BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OR INABILITY TO USE THE PRODUCT, OR FROM DELAY IN THE REPLACEMENT OR REPAIR OF PRODUCTS UNDER THE ABOVE WARRANT

Polyonics World Headquarters

28 Industrial Park Drive
Westmoreland, NH 03467
Ph: 603.352.1415
Fax: 603.352.1936
Email: info@polyonics.com

Polyonics Asia

Fuweo Mansion Rm 411
Hongtu Road 88
Nancheng District
Dongguan, Guangdong, China 523078
Ph: 86.755.8825.0441
Fax: 86.755.8825.2429
Email: infoasia@polyonics.com